

Process Oil Series

Product Overview

- Paraffin oil (Paraffinic Oils) : **P-1, 2, 3, 4**
- Naphthenic five days (Naphthenic Oils) :
- Aromatic oils (Aromatic Oils) :

Product Features

- Fit the rubber and chemical processes refined Paraffinic Process Oil,
- Chemical: Paraffinic Side Carbon at least 50% of the entire carbon in Chains,
- Stable to light and heat for Color, light-colored and white goods manufacturing and optimum color change as the process of oil products.
- Aromatic oils, naphthenic Volatility is good compared to the oil and non-staining, robustness to cold.
- Natural rubber, SBR, BR, EPDM, etc. can be used for almost all combinations of the object.
- Exothermic used for small vulcanized rubber products.

Process Oil Series

Separation	Specific Gravity 15/4°C	Kinematic Viscosity cSt 40 °C	Flash Point °C	Aniline Point, °C	Pour Point °C	Color ASTM	Corrosive Test (100°C×3h)	Total Acid Value mgKOH/g
P-1	0.865	7.30	165	80	-17.5	L0.5	1a	0.01
P-2	0.867	22.5	220	92	-17.5	L0.5	1a	0.01
P-3	0.782	45.7	210	115	-17.5	L1.5	1a	0.01
P-4	0.875	96.0	230	110	-17.0	L1.5	1a	0.01